

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 October 2001 (18.10.2001)

PCT

(10) International Publication Number
WO 01/77241 A2

(51) International Patent Classification⁷: C09G 1/00

San Jose, CA 95129 (US). REDEKER, Fred, C.; 1801
Sioux Drive, Fremont, CA 94539 (US).

(21) International Application Number: PCT/US01/11075

(74) Agent: PATTERSON, William, B.; Thomason, Moser
& Patterson, LLP, Suite 1500, 3040 Post Oak Boulevard,
Houston, TX 77056 (US).

(22) International Filing Date: 5 April 2001 (05.04.2001)

(25) Filing Language:

English

(81) Designated States (national): JP, KR.

(26) Publication Language:

English

(84) Designated States (regional): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE, TR).

(30) Priority Data:

09/543,777

5 April 2000 (05.04.2000) US

Published:

— without international search report and to be republished
upon receipt of that report

(71) Applicant: APPLIED MATERIALS, INC. [US/US];
3050 Bowers Avenue, Santa Clara, CA 94054 (US).


(72) Inventors: SUN, Lizhong; 952 Windsor Hills Circle, San
Jose, CA 95123 (US). LI, Shijian; 1202 Donington Drive,

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



WO 01/77241 A2

(54) Title: COMPOSITION FOR METAL CMP WITH LOW DISHING AND OVERPOLISH INSENSITIVITY



(57) Abstract: Polishing compositions for metal CMP
with reduced dishing and overpolish insensitivity are
formulated to have a low static etching rate at high
temperatures, e.g., higher than 50 °C. Embodiments include
abrasive-free polishing compositions comprising one or
more chelating agents, one or more oxidizers, one or more
corrosion inhibitors, one or more acids to achieve a pH of
about 3 to about 10 and deionized water.

COMPOSITION FOR METAL CMP WITH LOW DISHING AND OVERPOLISH INSENSITIVITY

TECHNICAL FIELD

The present invention relates generally to metal polishing and, particularly, to planarizing copper (Cu) and/or Cu alloy metallization in manufacturing semiconductor devices with reduced dishing and overpolish insensitivity. The present invention is applicable to manufacturing high speed integrated circuits having submicron design features and high conductivity interconnect structures with improved reliability.

BACKGROUND ART

The escalating requirements for high density and performance associated with ultra large scale integration semiconductor wiring require responsive changes in interconnection technology. Such escalating requirements have been found difficult to satisfy in terms of providing a low RC (resistance and capacitance) interconnect pattern, particularly wherein submicron vias, contacts and conductive lines have high aspect ratios imposed by miniaturization.

Conventional semiconductor devices comprise a semiconductor substrate, typically doped monocrystalline silicon, and a plurality of sequentially formed interlayer dielectrics and conductive patterns. An integrated circuit is formed containing a plurality of conductive patterns comprising conductive lines separated by interwiring spacings, and a plurality of interconnect lines, such as bus lines, bit lines, word lines and logic interconnect lines. Typically, the conductive patterns on different layers, i.e., upper and lower layers, are electrically connected by a conductive plug filling a via hole, while a conductive plug filling a contact hole establishes electrical contact with an active region on a semiconductor substrate, such as a source/drain region. Conductive lines are formed in trenches which typically extend substantially horizontal with respect to the semiconductor substrate. Semiconductor "chips" comprising five or more levels of metallization are becoming more prevalent as device geometries shrink to submicron levels.

A conductive plug filling a via hole is typically formed by depositing an interlayer dielectric on a conductive layer comprising at least one conductive pattern, forming an opening through the interlayer dielectric by conventional photolithographic and etching

techniques, and filling the opening with a conductive material, such as tungsten (W). Excess conductive material on the surface of the dielectric interlayer is typically removed by chemical mechanical polishing (CMP). One such method is known as damascene and basically involves forming an opening in the dielectric interlayer and filling the opening with a metal. Dual damascene techniques involve forming an opening comprising a lower contact or via hole section in communication with an upper trench section. The entire opening is filled with a conductive material, typically a metal, to simultaneously form a conductive plug in electrical contact with a conductive line.

Cu and Cu alloys have received considerable attention as a candidate for replacing Al in interconnect metallizations. Cu is relatively inexpensive, easy to process, and has a lower resistivity than Al. In addition, Cu has improved electrical properties vis-à-vis W, making Cu a desirable metal for use as a conductive plug as well as conductive wiring.

An approach to forming Cu plugs and wiring comprises the use of damascene structures employing CMP. However, due to Cu diffusion through interdielectric layer materials, such as silicon dioxide, Cu interconnect structures must be encapsulated by a diffusion barrier layer. Typical diffusion barrier metals include tantalum (Ta), tantalum nitride (Ta₃N₅), titanium nitride (TiN), titanium-tungsten (TiW), tungsten (W), tungsten nitride (WN), titanium-titanium nitride (Ti-TiN), titanium silicon nitride (TiSiN), tungsten silicon nitride (WSiN), tantalum silicon nitride (TaSiN) and silicon nitride for encapsulating Cu. The use of such barrier metals to encapsulate Cu is not limited to the interface between Cu and the dielectric interlayer, but includes interfaces with other metals as well.

In conventional CMP techniques, a wafer carrier assembly is in contact with a polishing pad in a CMP apparatus. The wafers are typically mounted on a carrier or polishing head which provides a controllable pressure urging the wafers against the polishing pad. The pad has a relative movement with respect to the wafer driven by an external driving force. Thus, the CMP apparatus effects polishing or rubbing movement between the surface of each thin semiconductor wafer and the polishing pad while dispersing a polishing slurry containing abrasive particles in a reactive solution to effect both chemical activity and mechanical activity while applying a force between the wafer and a polishing pad. A different type of abrasive article from the above-mentioned abrasive slurry-type polishing pad is fixed abrasive article, e.g., fixed abrasive polishing pad. Such a fixed abrasive article typically comprises a backing sheet with a plurality of geometric abrasive composite elements adhered thereto.

It is extremely difficult to planarize a metal surface, particularly a Cu surface, as by CMP of a damascene inlay, with a high degree of surface planarity. A dense array of Cu features is typically formed in an interlayer dielectric, such as a silicon oxide layer, by a damascene technique wherein trenches are initially formed. A barrier layer, such as a Ta-containing layer e.g., Ta, TaN, is then deposited lining the trenches and on the upper surface of the silicon oxide interlayer dielectric. Cu or a Cu alloy is then deposited, as by electroplating, electroless plating, physical vapor deposition (PVD) at a temperature of about 50°C to about 150°C or chemical vapor deposition (CVD) at a temperature under about 200°C, typically at a thickness of about 8,000Å to about 18,000Å. CMP is then conducted to remove the Cu or Cu alloy overburden stopping on the barrier layer. Buffing is then conducted to remove the barrier layer, employing a mixture of a chemical agent and abrasive particles, leaving a Cu or the Cu alloy filling the damascene opening with an exposed surface. Overpolishing, as at about 10% to about 25%, is typically conducted beyond the time required to reach the targeted layer, as determined by conventional end point detection techniques, e.g., to completely remove the Cu or Cu alloy. For example, if 300 seconds of polishing are required to reach the interlayer dielectric, 20% overpolishing would involve a total polishing time of 360 seconds. Conventional CMP techniques employing polishing pads utilizing slurries containing abrasive particles as well as CMP techniques employing fixed abrasive articles are characterized by excessive dishing and sensitivity to overpolishing.

Dishing occurs wherein a portion of the surface of the inlaid metal of the interconnection formed in the groove in the interlayer dielectric is excessively polished resulting in one or more concavities or depressions. For example, adverting to Fig. 1, conductive lines 11 and 12 are formed by depositing a metal, such as Cu or a Cu alloy, in a damascene opening formed in interlayer dielectric 10, e.g., silicon dioxide. Subsequent to planarization, a portion of the inlaid metal 12 is depressed by an amount D referred to as the amount of dishing. For example, dishing occurring in metal lines, such as Cu or Cu alloy metal lines having a width of about 50 microns, generally exceeds 1,000Å with as little overpolish as about 5% to about 10%.

Another phenomenon resulting from conventional planarization techniques is known as erosion which is characterized by excessive polishing of the layer not targeted for removal. For example, adverting to Fig. 2, metal line 21 and dense array of metal lines 22

are inlaid in interlayer dielectric 20. Subsequent to planarization, excessive polishing of the interlayer material results in erosion E.

Dishing disadvantageously results in a non-planar surface that impairs the ability to print high resolution lines during subsequent photolithographic steps. Dishing can also
5 cause the formation of short circuits or open circuits in the metal interconnection formed thereover. Moreover, dishing increases when overpolishing is conducted to ensure complete removal of the metal layer and/or barrier layer across the wafer surface.

There exists a need for a polishing composition enabling the planarization of inlaid metal, particularly inlaid Cu metallization, with reduced dishing and insensitivity to
10 overpolishing.

DISCLOSURE OF THE INVENTION

An aspect of the present invention is a polishing composition suitable for planarizing metals, such as Cu and Cu alloys, with significantly reduced dishing and significantly reduced sensitivity to overpolish.

15 According to the present invention, the foregoing and other aspects are achieved in part by a composition for chemical mechanical polishing (CMP) a surface containing a metal, the composition comprising: one or more chelating agents; one or more oxidizers, one or more corrosion inhibitors; one or more acids; and deionized water.

Embodiments of the present invention comprise a polishing composition having a
20 low static etching rate with respect to Cu. Embodiments of the present invention include polishing compositions comprising one or more chelating agents, such as ethylenediaminetetraacetic acid, ethylenediamine or methylformamide, one or more oxidizers, such as hydrogen peroxide, ferric nitrate or an iodate, one or more corrosion inhibitors, such as benzotriazole, mercaptobenzotriazole or 5-methyl-1-benzotriazole, one or
25 more acids, such as an inorganic or organic acid sufficient to achieve a pH of about 3 to about 10, such as a pH of about 5 to about 8 e.g., acetic acid, phosphoric acid or nitric acid, the remainder deionized water.

Additional aspects of the present invention will become readily apparent to those skilled in this art from the following detailed description, wherein embodiments of the
30 present invention are described, simply by way of illustration of the best mode contemplated for carrying out the present invention. As will be realized, the present invention is capable of other and different embodiments, and its several details are capable

of modifications in various obvious respects, all without departing from the present invention. Accordingly, the drawings and description are to be regarded as illustrative in nature, and not as restrictive.

BRIEF DESCRIPTION OF DRAWINGS

5 Fig. 1 schematically illustrates the phenomenon of dishing.

Fig. 2 schematically illustrates the phenomenon of erosion.

Figs. 3-5 schematically illustrate sequential phases of a method employing a composition in accordance with an embodiment of the present invention.

DESCRIPTION OF THE INVENTION

10 The present invention provides a polishing composition that enables effective and efficient planarization of metallization, e.g., Cu metallization, with significantly reduced dishing and significantly reduced overpolishing sensitivity. Such disadvantages include the impairment of the ability to print high resolution lines during photolithographic processing and the formation of shorts or open circuits in the interconnection formed thereover. As
15 used throughout this disclosure, the symbol Cu is intended to encompass high purity elemental copper as well copper-based alloys, e.g., copper-based alloys containing at least about 80 at.% copper.

The aspects of the present invention are achieved with a polishing composition strategically formulated such that it exhibits a reduced static etching rate, i.e., etching rate in
20 the absence of mechanical abrasion, even at elevated temperatures, thereby reducing dishing. In addition, it was found that polishing compositions in accordance with the present invention advantageously generate polishing by-products which are not only smaller than abrasives applied during conventional CMP and fixed abrasive CMP but also relatively softer and, hence, provide a smooth and stable polish and a finished surface which
25 exhibits reduced defects.

Conventional slurries for conventional CMP methodology as well as polishing compositions for fixed abrasive CMP methodology exhibit relatively high static etching rates and relatively high sensitivity to overpolishing, both of which lead to excessive dishing. The present invention overcomes problems attendant upon high dishing and high
30 overpolishing sensitivity by providing polishing compositions formulated with a relatively low static etching rate for a particular material undergoing CMP. For example,

conventional CMP methodology employing abrasive slurries exhibit a Cu static etching rate greater than 300Å per minute at 52°C and greater than 730Å per minute at 52°C for fixed abrasive copper CMP. Dishing in 50 micron conductive lines exceeds 1,000Å with very little overpolish, e.g., about 5% to about 10%, for both conventional Cu CMP and fixed
5 abrasive CMP.

In accordance with the present invention, polishing compositions are formulated that exhibit a static etching rate less than about 200Å per minute at 52°C. Polishing compositions in accordance with the present invention enable CMP with dishing of 50 micron lines less than 520Å even with as high as 30% to 50% overpolishing using fixed
10 abrasive pads, and less than about 600Å with 58% overpolishing using conventional pads.

In accordance with the present invention, polishing compositions suitable for use with abrasive-free copper CMP, conventional slurry copper CMP and fixed abrasive copper CMP comprise one or more chelating agents, such as a chelating agent containing one or more amine or amide groups, e.g., ethylenediaminetetraacetic, ethylenediamine or
15 methylformamide. The chelating agents can be present in a suitable amount, such as about 0.2 wt.% to about 3.0 wt.%. The compositions in accordance with the present invention further comprise one or more oxidizers, one or more corrosion inhibitors, one or more acids and deionized water. The oxidizers can comprise any of various conventional oxidizers employed in CMP, such as hydrogen peroxide, ferric nitrate or an iodate, and can be present
20 in a suitable amount, such as about 0.5 wt.% to about 8.0 wt.%. The corrosion inhibitors can comprise any various organic compounds containing one or more azole groups, such as benzotriazole, mercaptobenzotriazole, or 5-methyl-1-benzotriazole, and can be present in a suitable amount, such as about 0.02 wt.% to about 1.0 wt.%. The acid or acids are present
25 in an amount for adjusting the pH of the composition to a range of about 3 to about 10 and can comprise any of various inorganic and/or organic acids, such as acetic acid, phosphoric acid, or oxalic acid. In formulating polishing compositions for use with conventional abrasive slurry-type CMP, conventional abrasive particles can be incorporated in a suitable amount up to about 40% wt.%, such as about 0.1 wt.% to about 40%, e.g., about 0.5 to about 30 wt.%.

30 Embodiments of the present invention comprise polishing compositions enabling CMP of Cu, without removing a barrier layer, and overpolishing, e.g., up to 50% and even longer.

A CMP technique employing a polishing composition in accordance with an embodiment of the present invention is schematically illustrated in Figs. 3-5, wherein similar features bear similar reference numerals. Adverting to Fig. 3, interlayer dielectric 40, e.g., silicon oxide, is formed overlying a substrate (not shown). A plurality of openings 41 are formed in a designated area A in which a dense array of conductive lines are to be formed bordering an open field B. A barrier layer 42, e.g., TaN, is deposited lining the openings 41 and on the upper surface of silicon oxide interlayer dielectric 40. Typically, the openings 41 are spaced apart by a distance C which is less than about 1 micron, e.g., about 0.2 micron. Cu layer 43 is then deposited at a thickness D of about 8,000Å to about 18,000Å.

Adverting to Fig. 4, CMP is conducted employing an abrasive-free polishing composition in accordance with the present invention to remove the Cu overburden stopping on TaN barrier layer 42, employing a conventional end point detection technique, with significantly reduced dishing. As shown in Fig. 5, buffing is conducted to remove the barrier layer and reduce defects. The resulting Cu interconnection structure comprises a dense array A of Cu lines 43 bordered by open field B. The upper surface 60 of the Cu metallization exhibits significantly reduced dishing.

Polishing compositions in accordance with the present invention are applicable to planarizing a wafer surface during various stages of semiconductor manufacturing by any of various CMP techniques, including abrasive-free CMP, using any of various CMP systems and polishing articles, e.g., fixed abrasive- or abrasive slurry-type pads or sheets. The present invention enjoys particular applicability in the manufacture of high density semiconductor devices with metal features in the deep submicron range.

Only the preferred embodiment of the present invention and but a few examples of its versatility are shown and described in the present disclosure. It is to be understood that the present invention is capable of use in various other combinations and environments and is capable of changes and modifications within the scope of the inventive concept as expressed herein.

WHAT IS CLAIMED IS:

1. A composition for chemical mechanical polishing (CMP) a surface containing a metal, the composition having a static etching rate of no greater than about 200Å per minute at about 52°C and comprising:

one or more chelating agents;

5

one or more oxidizers;

one or more corrosion inhibitors;

one or more acids; and

deionized water.

2. The composition according to claim 1, wherein the metal is copper (Cu) or a Cu alloy.

3. The composition according to claim 2, having a pH of about 3.0 to about 10.0.

4. The composition according to claim 3, comprising:

about 0.2 to about 3.0 wt.% of one or more chelating agents;

about 0.5 to about 8.0 wt.% of one or more oxidizers;

about 0.02 to about 1.0 wt.% of one or more corrosion inhibitors;

5 an amount of acid sufficient to achieve a pH of about 3.0 to about 10.0; and
the remainder deionized water.

5. The composition according to claim 4, comprising:

at least one chelating agent having at least one amine or amide group;

at least one oxidizer comprising hydrogen peroxide, ferric nitrate or an iodate;

at least one corrosion inhibitor comprising at least one azole group; and

5

at least one inorganic or organic acid.

6. The composition according to claim 5, comprising:

ethylenediaminetetraacetic acid, ethylenediamine or methylformamide as a chelating agent;

5 benzotriazole, mercaptobenzothiazole or 5-methyl-1-benzotriazole as a corrosion inhibitor; and

acetic acid, phosphoric acid, or oxalic acid as an acid.

7. The composition according to claim 3, further comprising up to about 40 wt.% of abrasive particles.

8. The composition according to claim 7, comprising about 0.5 to about 30 wt.% of abrasive particles.

9. A composition for chemical mechanical polishing (CMP) a surface containing a metal, the composition having a pH of about 3.0 to about 10.0 and comprising:

one or more chelating agents;

one or more oxidizers;

5 one or more corrosion inhibitors;

one or more acids; and

deionized water.

10. The composition according to claim 9, having a static etching rate of no greater than about 200Å per minute at about 52°C

11. The composition according to claim 9, wherein the metal is copper (Cu) or a Cu alloy.

12. The composition according to claim 9, comprising:

about 0.2 to about 3.0 wt.% of one or more chelating agents;

about 0.5 to about 8.0 wt.% of one or more oxidizers;

about 0.02 to about 1.0 wt.% of one or more corrosion inhibitors;

5 an amount of acid sufficient to achieve a pH of about 3.0 to about 10.0; and
the remainder deionized water.

13. The composition according to claim 9, comprising about 0.5 to about 30 wt.% of abrasive particles.

14. A composition for chemical mechanical polishing (CMP) a surface containing a metal, the composition and comprising:

about 0.2 to about 3.0 wt.% of one or more chelating agents;

about 0.5 to about 8.0 wt.% of one or more oxidizers;

5 about 0.02 to about 1.0 wt.% of one or more corrosion inhibitors;

an amount of acid sufficient to achieve a pH of about 3.0 to about 10.0; and
the remainder deionized water.

15. The composition according to claim 14, having a static etching rate of no greater than about 200Å per minute at about 52°C

16. The composition according to claim 14, wherein the metal is copper (Cu) or a Cu alloy.

17. The composition according to claim 14, comprising:
ethylenediaminetetraacetic acid, ethylenediamine or methylformamide as a chelating agent;

benzotriazole, mercaptobenzothiazole or 5-methyl-1-benzotriazole as a corrosion
5 inhibitor; and
acetic acid, phosphoric acid, or oxalic acid as an acid.

18. The composition according to claim 14, further comprising up to about 40 wt.% of abrasive particles.

1/2




FIG. 1




FIG. 2




FIG. 3

SUBSTITUTE SHEET (RULE 26)

2/2




FIG. 4

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 October 2001 (18.10.2001)

PCT

(10) International Publication Number
WO 01/77241 A3

- (51) International Patent Classification⁷: C09G 1/02 (74) Agent: PATTERSON, William, B.; Thomason, Moser & Patterson, LLP, Suite 1500, 3040 Post Oak Boulevard, Houston, TX 77056 (US).
- (21) International Application Number: PCT/US01/11075
- (22) International Filing Date: 5 April 2001 (05.04.2001) (81) Designated States (national): JP, KR.
- (25) Filing Language: English (84) Designated States (regional): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- (26) Publication Language: English
- (30) Priority Data: 09/543,777 5 April 2000 (05.04.2000) US Published: — with international search report
- (71) Applicant: APPLIED MATERIALS, INC. [US/US]; 3050 Bowers Avenue, Santa Clara, CA 94054 (US). (88) Date of publication of the international search report: 7 February 2002
- (72) Inventors: SUN, Lizhong; 952 Windsor Hills Circle, San Jose, CA 95123 (US). LI, Shijian; 1202 Donington Drive, San Jose, CA 95129 (US). REDEKER, Fred, C.; 1801 Sioux Drive, Fremont, CA 94539 (US).
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 01/77241 A3

(54) Title: COMPOSITION FOR METAL CMP WITH LOW DISHING AND OVERPOLISH INSENSITIVITY

(57) Abstract: Polishing compositions for metal CMP with reduced dishing and overpolish insensitivity are formulated to have a low static etching rate at high temperatures, e.g., higher than 50 °C. Embodiments include abrasive-free polishing compositions comprising one or more chelating agents, one or more oxidizers, one or more corrosion inhibitors, one or more acids to achieve a pH of about 3 to about 10 and deionized water.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 01/11075

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09G1/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C09G H01L C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 49723 A (WOOD THOMAS E ;HARDY L CHARLES (US); KAISAKI DAVID A (US); KRANZ H) 5 November 1998 (1998-11-05) page 20, line 27 -page 3, line 10 page 23, line 13-22 page 24, line 10-14 page 25, line 1-13 page 25, line 14-20	1-9, 11-14, 16-18
A	WO 00 00561 A (CABOT CORP) 6 January 2000 (2000-01-06) page 4, line 23-25 claims 1-26 table 4	1-18

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

28 September 2001

Date of mailing of the international search report

10/10/2001

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Miller, A

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/11075

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
WO 9849723	A	05-11-1998	AU	734883 B2	21-06-2001
			AU	7170698 A	24-11-1998
			BR	9809311 A	04-07-2000
			CN	1254441 T	24-05-2000
			EP	1016133 A1	05-07-2000
			WO	9849723 A1	05-11-1998
<hr/>					
WO 0000561	A	06-01-2000	US	6217416 B1	17-04-2001
			AU	4723499 A	17-01-2000
			CN	1312843 T	12-09-2001
			EP	1090083 A1	11-04-2001
			WO	0000561 A1	06-01-2000
<hr/>					

THIS PAGE BLANK (USPTO)